



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08B 31/00, C08J 3/12, C08L 3/02, C08B 30/12	A1	(11) International Publication Number: WO 00/69916 (43) International Publication Date: 23 November 2000 (23.11.00)
<p>(21) International Application Number: PCT/NL00/00050</p> <p>(22) International Filing Date: 25 January 2000 (25.01.00)</p> <p>(30) Priority Data: 99200203.0 25 January 1999 (25.01.99) EP</p> <p>(71) Applicant (for all designated States except US): ATO B.V. [NL/NL]; P.O. Box 17, NL-6700 AA Wageningen (NL).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): GIEZEN, Franciscus, Egenius [NL/NL]; Nachtegaalstraat 74a, NL-3581 AM Utrecht (NL). JONGBOOM, Remigius, Oene, Jules [NL/NL]; Damstraat 28, NL-6671 AE Zetten (NL). FEIL, Herman [NL/NL]; De Gheijnstraat 10, NL-6717 RG Ede (NL). GOTLIEB, Kornelis, Fester [NL/NL]; Stoepveldsingel 119, NL-9403 SM Assen (NL). BOERSMA, Arjen [NL/NL]; Mr. Van Merwicklaan 3, NL-5237 KL Den Bosch (NL).</p> <p>(74) Agent: JORRITSMA, Ruurd; Nederlandsch Octrooibureau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: BIOPOLYMER NANOPARTICLES</p> <p>(57) Abstract</p> <p>A process for producing biopolymer nanoparticles is described, in which the biopolymer is plasticised using shear forces, a crosslinking agent being added during the processing. After said processing, the biopolymer can be dissolved or dispersed in an aqueous medium to a concentration between 4 and 40 wt.%. This results in starch nanoparticles which are characterised by an average particle size of less than 400 nm.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Biopolymer nanoparticles

[0001] The invention relates to a process for producing nanoparticles, i.e. particles essentially consisting of a biopolymer such as starch. The invention also relates to nanoparticles obtainable by such a process.

[0002] US 5,116,890 discloses self-crosslinking latices on the basis of a starch emulsion polymer graft. These latices require undesirable chemicals and are too hydrophobic for many applications.

[0003] It was found that biopolymers such as starch and other polysaccharides such as cellulose and gums, as well as proteins (e.g. gelatin, whey protein) can be formed into nanoparticles by processing the biopolymer using shear forces and simultaneous cross-linking. The biopolymers may be previously modified, e.g. with cationic groups, carboxymethyl groups, by acylation, phosphorylation, hydroxyalkylation, oxidation and the like. Starch and mixtures of starch with other (bio)polymers containing at least 50% starch are preferred. The biopolymer preferably has a dry substance content of at least 50%, especially at least 60 %by weight at the time when processing starts.

[0004] Processing using shear forces according to the invention means a mechanical treatment, which is in particular an extrusion treatment performed at elevated temperature (above 40°C, especially above 60°C, below the degradation point of the polymer, up to e.g. 200°C, especially up to 140°C) under conditions of high shear. The shear can be effected by applying at least 100 J of specific mechanical energy (SME) per g of biopolymer. Depending on the processing apparatus used the minimum energy may be higher; also when non-pregelatinised material is used, the minimum SME may be higher, e.g. at least 250 J/g, especially at least 500 J/g.

[0005] The mechanical treatment is conveniently performed at elevated temperature. The elevated temperature may be moderated, in case of starch, by using an alkaline medium or by using pregelatinised starch. During the mechanical treatment, the biopolymer is present in high concentration, especially a concentration of at least 40, more preferably at least 50 wt.%, in an aqueous solvent, such as water or a water/alcohol mixture. High pressure (e.g. between 5 and 150 bar) may be applied to facilitate processing at high concentrations.

[0006] A plasticiser may be present in addition to the water or water/alcohol mixture, such as a polyol (ethyleneglycol, propyleneglycol, polyglycols, glycerol, sugar alcohols, urea, citric acid esters, etc.) at a level of 5-40 % by weight of the biopolymer. However, water can already act as a plasticiser. The total amount of plasticisers (i.e. water and other

such as glycerol) is preferably between 15 and 50%. A lubricant, such as lecithin, other phospholipids or monoglycerids, may also be present, e.g. at a level of 0.5-2.5 % by weight. An acid, preferably a solid or semi-solid organic acid, such as maleic acid, citric acid, oxalic, lactic, gluconic acid, or a carbohydrate-degrading enzyme, such as amylase, may be present at a level of 0.01 –5 % by weight of biopolymer; the acid or enzyme assists in slight depolymerisation which is assumed to be advantageous in the process of producing nanoparticles of a specific size.

[0007] An essential step in the process of the invention is the crosslinking during the mechanical treatment. The crosslinking is preferably reversible, i.e. the crosslinks are partly or wholly cleaved after the mechanical treatment step. Suitable reversible crosslinkers include those which form chemical bonds at low water concentrations, which dissociate or hydrolyse in the presence of higher water concentrations. This mode of crosslinking results in a temporary high viscosity during processing followed by a lower viscosity after processing.

[0008] Examples of reversible crosslinkers are dialdehydes and polyaldehydes, which reversibly form hemiacetals, acid anhydrides and mixed anhydrides (e.g. succinic and acetic anhydride) and the like. Suitable dialdehydes and polyaldehydes are glutaraldehyde, glyoxal, periodate-oxidised carbohydrates, and the like. Glyoxal is a particularly suitable crosslinker for the purpose of the invention.

[0009] Such crosslinkers may be used alone or as a mixture of reversible crosslinkers, or as a mixture of reversible and non-reversible crosslinkers. Thus, conventional crosslinkers such as epichlorohydrin and other epoxides, triphosphates, divinyl sulphone, can be used as non-reversible crosslinkers for polysaccharide biopolymers, while dialdehydes, thiol reagents and the like may be used for proteinaceous biopolymers. The crosslinking reaction may be acid- or base-catalysed. The level of crosslinking agent can conveniently be between 0.1 and 10 weight % with respect to the biopolymer. The crosslinking agent may already be present at the start of the mechanical treatment, but in case of a non-pre-gelatinised biopolymer such as granular starch, it is preferred that the crosslinking agent is added later on, i.e. during the mechanical treatment.

[0010] The mechanically treated, crosslinked biopolymer is then formed into a latex by dispersion in a suitable solvent, usually water and/or another hydroxylic solvent such as an alcohol), to a concentration of between 4 and 50 wt.% especially between 10 and 40 wt.%. Prior to the dispersion a cryogenic grinding step may be performed, but stirring with mild heating may work equally well. This treatment results in a gel which either spontaneously

or after induction by water adsorption, is broken into a latex. This viscosity behaviour can be utilised for applications of the particles, such as improved mixing, etc. If desired, the dispersed biopolymer may be further crosslinked, using the same or other crosslinking agents as describe above.

5 [0011] The invention pertains to an extrudate obtained by plasticising a biopolymer, in particular starch, and crosslinking it as described above. The extrudate is characterised by swelling in an aqueous solvent, e.g. water or a mixture of at least 50% water with a water-miscible solvent such as an alcohol, and by exhibiting a viscosity drop afterwards to produce a dispersion of nanoparticles.

10 [0012] The invention also pertains to the nanoparticles obtainable from the extrudate referred to above. The nanoparticles (as such or as a dispersion) are characterised by their small particle size of below 400 nm, especially below 200 nm, their stability, narrow particle size distribution and viscosity. The narrow particle distribution is in particular reflected by the ratio of weight-averaged molecular weight to number-averaged molecular weight being below 2 ($M_w/M_n < 2$).

15 [0013] The nanoparticles can be used as a matrix material i.e. as a resin e.g. in coating applications wherein an increased dry solids content is desired. Such matrix materials may be a film-forming material (for adjusting the minimum film-forming temperature), a thickener, or a rheology modifier, or an adhesive or an adhesive additive (tackifier). As a
20 thickener, it may have higher viscosities, e.g. greater than 150 mPas. The nanoparticles or dispersions thereof may also be used for their barrier properties (high barrier for e.g. oxygen, low barrier e.g. for water), as a carrier (e.g. for colorants, medicaments, flavours and fragrances and the like, advantageously as a slow-release agent), as a fat replacer (due to their mouth-feel), in cosmetic compositions (lack of allergenic properties) etc., as a
25 medicament for mitigating dermal disorders, burns and the like. Further examples of such applications are in the paper-making and packaging industry (paper and cardboard surface treatment, gloss etc.), or in agriculture and horticulture (protective layers on e.g. bulbs, and other plant arts), or as removable or temporary coatings for protection purposes. The nanoparticles can also be used as excipients or carriers e.g. in medicines, where they may be
30 complexed or covalently coupled to active substances such as slow-release drugs. The nanoparticles can also be processed into a foam at relatively high density.

Description of the figure

The figure shows two screw configurations of the extruder used in the examples.

Example 1*Extrusion*

[0014] A premix of native potato starch (12.6 kg, moisture content 18%, Avebe) and glycerol (2.4 kg = 16 wt.% of premix) was prepared at room temperature in a Bear Varimixer for 15 minutes to produce a homogeneous premix. The premix was fed into an extruder (Berstorff ZE40 self-wiping, co-rotating twin screw extruder, 38D) at a rate of 8.4 kg/hr with a K-Tron K2M &85 volumetric feeder. The extruder has 9 zones with an adjusted temperature profile of 20-80-90-100-100-100-100-100-95 °C. Screw configuration 1 (Figure) was used. The screw speed was set at 160 rpm. A 5 wt.% solution of glyoxal in water was injected in the barrel at the 5th zone (22D), at a flow rate of 1.2 kg/hr with a Prominent Meta HK20-12,5S piston dosing pump. As a result, the pure glyoxal percentage in relation to the dry amount of starch was 1%. The extrudate left the extruder through a five-hole die (diameter of holes 3 mm) and was subsequently granulated.

Latex preparation (1)

[0015] The granules were cryogenically ground and sieved to obtain particles smaller than 150 µm. Subsequently, this powder was mixed with water. The amount of powder was adjusted to the desired solid load in the final dispersion. After stirring the mixture at room temperature, a strong gel was formed. This gel collapsed after some time, and a low-viscous homogeneous transparent light-brown dispersion was formed. The viscosity of 10w/w% dispersion was measured with a Brookfield DV-III Viscometer, showing a viscosity of 26 mPa.s at a shear rate of 55 s⁻¹ at room temperature. The particle radii in a 10 w/w% dispersion were determined by means of DLS (Dynamic Light Scattering), showing values between 10 nm and 500 nm, and a calculated average particle radius of 54 nm.

Latex preparation (2)

[0016] The granules were cryogenically ground and sieved to obtain particles smaller than 500 µm. 10 g of this powder was mixed with 90 g of water. After stirring the mixture at room temperature, a strong gel was formed. This gel collapsed after some time, and a low-viscous homogeneous transparent light-brown dispersion was formed. The particle radii were determined by means of DLS (Dynamic Light Scattering), showing values between 10 nm and 500 nm.

Latex preparation (3)

[0017] 10 g of the granules were mixed with 90 g of water. After stirring the mixture at 50 °C for 2 hr a low viscous dispersion was formed. After filtering of the dispersion over a

150 μm filter cloth the particle sizes were determined by means of DLS, showing radii between 10 nm and 500 nm.

Latex preparation (4)

[0018] 20 g of the granules were mixed with 80 g of water. After stirring the mixture at 50 °C for 2 hr a low viscous dispersion was formed. After filtering of the dispersion over a 150 μm filter cloth the viscosity of the dispersion was determined with a Brookfield DV-III Viscometer, showing a viscosity of 825 mPa.s at a shear rate of 55 s^{-1} at room temperature.

Film formation

[0019] The dispersion obtained above (20 g) was casted into a polystyrene tray (casting onto glass, paper is also feasible) and subsequently dried at room temperature. After two days a transparent strong starch film remained.

Examples 2-6

[0020] Example 1 was repeated in a continuous mode: 8.81 kg of premix (containing 6.48 kg of dry potato starch, 18.0 wt.% = 1.17 kg of water and 17.9 wt.% = 1.16 kg of glycerol) was fed per hour. A glyoxal solution containing 5-10-15 wt.% of glyoxal in water (0.93-1.86-2.80 wt.% with respect to dry starch) was fed at a rate of 1.2 kg/hour. The results are presented in the following table.

Table

[0021] Results of continuous thermomechanical treatment and crosslinking

example	2	3	4	5	6
X-link wt.% ¹	10	15	5	10	10
screw speed	200	200	100	100	250
screw conf. ²	1	1	1	1	2
SME (J/g)	1765	1818	972	1186	3316
viscosity ³ mPas	27.8	17.0	185.0	118.3	17.5
particle radius nm	42.5	36.9	101.4	53.4	41.9

¹: concentration of crosslinker in water (1% corresponding to about 0.186 wt.% with respect to dry starch)

²: see accompanying figure

³: determined of a 10% dispersion at 186 s^{-1} and 20°C

Example 7

[0022] A premix of waxy corn starch (moisture content 11.5 %, Meritena 300, Amylum), glycerol (18 %, based on dry starch) and water (total water content adjusted to 22 %, based on dry starch) was fed into the feeding zone of a Berstorff ZE40 extruder ($L/D = 38$) at a rate of 8.8 kg/h. The temperature profile in the extruder was similar to the one described in example 1. Screw configuration 1 was used and the screw speed was set on 200 rpm. A glyoxal solution of 10 % in water was fed in the 5th zone (22D) at a rate of 1.2 kg/h. The extrudate was dried and granulated. Dispersion preparation was performed as described in example 1 (latex preparation 1). A 20 % dispersion was obtained having a Brookfield viscosity of 225 mPas at a shear rate of 20 s^{-1} .

Example 8

[0023] A premix of waxy rice starch (moisture content 14 %, Remyline AX-DR, Remy), glycerol (18 %, based on dry starch) and water (total water content adjusted to 22 %, based on dry starch) was fed into the feeding zone of a Berstorff ZE40 extruder ($L/D = 38$) at a rate of 8.8 kg/h. The temperature profile in the extruder was similar to the one described in example 1. Screw configuration 1 was used and the screw speed was set on 200 rpm. A glyoxal solution of 10 % in water was fed in the 5th zone (22D) at a rate of 1.2 kg/h. The extrudate was dried and granulated. Dispersion preparation was performed as described in example 1 (latex preparation 1). A 20 % dispersion was obtained having a Brookfield viscosity of 253 mPas at a shear rate of 20 s^{-1} .

Example 9

[0024] A premix of modified (acetylated and crosslinked) waxy corn starch (moisture content 12.7 %, Resistamyl 342, Amylum), glycerol (18 %, based on dry starch) and water (total water content adjusted to 22 %, based on dry starch) was fed into the feeding zone of a Berstorff ZE40 extruder ($L/D = 38$) at a rate of 8.8 kg/h. The temperature profile in the extruder was similar to the one described in example 1. Screw configuration 1 was used and the screw speed was set on 200 rpm. A glyoxal solution of 10 % in water was fed in the 5th zone (22D) at a rate of 1.2 kg/h. The extrudate was dried and granulated. Dispersion preparation was performed as described in example 1 (latex preparation 1). A 20 % dispersion was obtained having a Brookfield viscosity of 180 mPas at a shear rate of 20 s^{-1} .

Example 10

[0025] A premix of waxy corn starch (moisture content 11.5 %, Meritena 300, Amylum), glycerol (18 %, based on dry starch), water (total water content adjusted to 22 %, based on

dry starch) and maleic acid (0.5 % based on dry starch) was fed into the feeding zone of a Berstorff ZE40 extruder ($L/D = 38$) at a rate of 8.8 kg/h. The temperature profile in the extruder was similar to the one described in example 1. Screw configuration 2 was used and the screw speed was set on 200 rpm. A glyoxal solution of 10 % in water was fed in the 5th zone (22D) at a rate of 1.2 kg/h. The extrudate was dried and granulated. Dispersion preparation was performed as described in example 1 (latex preparation 1). A 35 % dispersion was obtained having a Brookfield viscosity of 1400 mPas at a shear rate of 20 s^{-1} .

Claims

1. A process for producing biopolymer nanoparticles, in which the biopolymer is plasticised by processing using shear forces, a crosslinking agent being present during the processing.
2. A process according to claim 1, wherein the biopolymer is starch or a starch derivative or a polymer mixture containing at least 50 % starch.
3. A process according to claim 1 or 2, wherein the crosslinking agent is a dialdehyde or polyaldehyde, especially glyoxal.
4. A process according to any one of claims 1-3, wherein the processing is carried out at a temperature of between 40 and 200°C.
5. A process according to any one of claims 1-3, wherein shear forces are used corresponding to a mechanical energy input of at least 100 J/g.
6. A process according to any one of the preceding claims, wherein the biopolymer has a dry substance content during processing of at least 50% by weight.
7. A process according to any one of the preceding claims, wherein the processing comprises extrusion.
8. A process according to any one of the preceding claims, wherein 1-40 wt.%, based on the weight of the biopolymer, of an additional plasticiser such as glycerol is present during the processing.
9. A process according to any one of the preceding claims, wherein 0.01-5 %, based on the weight of the biopolymer, of an acid such as maleic acid, oxalic acid or citric acid is present during processing.
10. A process according to any one of the preceding claims, wherein 0.01-5 %, based on the weight of the biopolymer, of an enzyme such as amylase is present during processing.


11. A process according to any one of the preceding claims, wherein after said processing, the biopolymer is dissolved or dispersed in an aqueous medium to a concentration between 4 and 40 wt.%.
12. A process according to claim 11, wherein the dispersion of the biopolymer is further crosslinked after said processing.
13. Starch nanoparticles which - optionally after dispersion in water - are characterised by an average particle size of less than 400 nm and a narrow particle size distribution ($M_w/M_n < 2$).
14. A dispersion of crosslinked starch nanoparticles according to claim 13 in water.
15. A dispersion according to claim 14, having a viscosity at a concentration of 10% by weight at 186 s^{-1} of below 150 mPas, preferably below 50 mPas.
16. A extrudate of crosslinked polymer containing at least 50% starch, which swells upon immersion in an aqueous medium and forms a low viscous dispersion after immersion.

Screw configuration 1



1/1

Screw configuration 2



INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 00/00050

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08B31/00 C08J3/12 C08L3/02 C08B30/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08B C08L C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, CHEM ABS Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR 2 265 762 A (HENKEL & CIE GMBH) 24 October 1975 (1975-10-24) page 1, line 34 - line 37 claims; examples ---	1-4, 6, 13
A	EP 0 118 240 A (WARNER-LAMBERT COMPANY) 12 September 1984 (1984-09-12) abstract page 23, line 25 - line 36 claim 3 ---	1-8
P, A	US 6 001 408 A (DUDACEK ET AL.) 14 December 1999 (1999-12-14) abstract; example 1 ---	1, 2, 4-8, 13
A	US 4 072 535 A (SHORT ET AL.) 7 February 1978 (1978-02-07) abstract ---	13
-/-		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 August 2000

Date of mailing of the international search report

18/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mazet, J-F

INTERNATIONAL SEARCH REPORT

Inte ional Application No
PCT/NL 00/00050

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 525 245 A (BUTTERFLY SRL.) 3 February 1993 (1993-02-03) page 4, line 38 - line 55 claim 1 ---	16
A	US 5 412 005 A (BASTIOLI ET AL.) 2 May 1995 (1995-05-02) column 1, line 24 - line 36 column 10, line 49 - line 67 -----	16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 00/00050

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2265762 A	24-10-1975	DE 2415556 A	16-10-1975
		JP 1268501 C	10-06-1985
		JP 50130838 A	16-10-1975
		JP 59045685 B	08-11-1984
		US 3997508 A	14-12-1976
		ZA 7501956 A	25-02-1976
EP 118240 A	12-09-1984	AT 44975 T	15-08-1989
		AU 572119 B	05-05-1988
		AU 2465684 A	23-08-1984
		BG 46154 A	16-10-1989
		BR 8400734 A	02-10-1984
		CA 1238738 A	28-06-1988
		CS 8401078 A	12-02-1987
		CS 8505547 A	12-02-1987
		DD 218113 A	30-01-1985
		DE 3479129 D	31-08-1989
		DK 76584 A	19-08-1984
		EG 17995 A	30-06-1992
		ES 529815 D	16-05-1985
		ES 8505385 A	01-09-1985
		FI 840614 A, B,	19-08-1984
		GR 82253 A	13-12-1984
		HU 36487 A, B	30-09-1985
		IE 56888 B	15-01-1992
		IL 70980 A	31-03-1987
		IN 160476 A	11-07-1987
		IN 165520 A	04-11-1989
		JP 1838984 C	25-04-1994
		JP 59196335 A	07-11-1984
		KR 9304937 B	10-06-1993
		MX 170518 B	27-08-1993
		NO 840598 A, B,	20-08-1984
		NZ 207188 A	10-09-1986
		PH 20759 A	10-04-1987
		PL 246259 A	13-02-1985
		PT 78123 A, B	01-03-1984
		RO 88123 A	30-11-1985
		RU 2042423 C	27-08-1995
		TR 23047 A	14-02-1989
		YU 28684 A	31-12-1986
		US 4673438 A	16-06-1987
		US 4738724 A	19-04-1988
US 6001408 A	14-12-1999	AU 707179 B	01-07-1999
		AU 6818396 A	17-04-1997
		CA 2187725 A	14-04-1997
		JP 9165401 A	24-06-1997
US 4072535 A	07-02-1978	NONE	
EP 525245 A	03-02-1993	AT 155161 T	15-07-1997
		AU 658180 B	06-04-1995
		AU 1650992 A	21-12-1992
		AU 658207 B	06-04-1995
		AU 2058292 A	04-02-1993
		BR 9203064 A	30-03-1993
		BR 9205258 A	27-07-1993

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 00/00050

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 525245 A		CA 2074649 A	02-02-1993
		CA 2084994 A	04-11-1992
		CN 1071588 A	05-05-1993
		CN 1077966 A, B	03-11-1993
		CZ 9202395 A	17-02-1993
		CZ 285748 B	13-10-1999
		DE 9219021 U	27-02-1997
		DE 69220754 D	14-08-1997
		DE 69220754 T	04-12-1997
		DE 539541 T	30-01-1997
		DK 539541 T	15-09-1997
		WO 9219680 A	12-11-1992
		EP 0539541 A	05-05-1993
		ES 2103943 T	01-10-1997
		FI 925978 A	31-12-1992
		GR 3024078 T	31-10-1997
		HU 216971 B	28-10-1999
		JP 5228205 A	07-09-1993
		JP 2527523 B	28-08-1996
		JP 6502676 T	24-03-1994
		KR 9608112 B	20-06-1996
		LV 12151 A	20-10-1998
		LV 12151 B	20-12-1998
		NO 925049 A	30-12-1992
		PL 295469 A	04-05-1993
		RU 2095379 C	10-11-1997
		SK 390192 A	07-12-1994
		RU 2089151 C	10-09-1997
		US 5286770 A	15-02-1994
		US 5412005 A	02-05-1995
US 5412005 A	02-05-1995	EP 0525245 A	03-02-1993
		IT 1245485 B	20-09-1994
		IT 1256693 B	12-12-1995
		IT 1263114 B	30-07-1996
		CN 1077966 A, B	03-11-1993
		IL 104942 A	10-06-1997
		AT 155161 T	15-07-1997
		AU 658180 B	06-04-1995
		AU 1650992 A	21-12-1992
		AU 658207 B	06-04-1995
		AU 2058292 A	04-02-1993
		BR 9203064 A	30-03-1993
		BR 9205258 A	27-07-1993
		CA 2074649 A	02-02-1993
		CA 2084994 A	04-11-1992
		CN 1071588 A	05-05-1993
		CZ 9202395 A	17-02-1993
		CZ 285748 B	13-10-1999
		DE 9219021 U	27-02-1997
		DE 69220754 D	14-08-1997
		DE 69220754 T	04-12-1997
		DE 539541 T	30-01-1997
		DK 539541 T	15-09-1997
		WO 9219680 A	12-11-1992
		EP 0539541 A	05-05-1993
		ES 2103943 T	01-10-1997
		FI 925978 A	31-12-1992

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/NL 00/00050

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5412005 A		GR 3024078 T	31-10-1997
		HU 216971 B	28-10-1999
		JP 5228205 A	07-09-1993
		JP 2527523 B	28-08-1996
		JP 6502676 T	24-03-1994
		KR 9608112 B	20-06-1996
		LV 12151 A	20-10-1998
		LV 12151 B	20-12-1998
		NO 925049 A	30-12-1992
		PL 295469 A	04-05-1993
		RU 2095379 C	10-11-1997
		SK 390192 A	07-12-1994
		RU 2089151 C	10-09-1997
		US 5286770 A	15-02-1994
		AT 127034 T	15-09-1995
		DE 69204351 D	05-10-1995
		DE 69204351 T	11-04-1996
		DK 512360 T	18-09-1995
		EP 0512360 A	11-11-1992
		ES 2077280 T	16-11-1995
		GR 3017583 T	31-12-1995
		JP 5123550 A	21-05-1993
		PL 174799 B	30-09-1998